


# TECHNICAL DATA SHEET

# SOFT FEEL DIGITAL - BMS035

**SOFT FEEL DIGITAL - BMS035** is a bioriented polypropylene film, with one side ultra-matt coated featuring a smooth tactile effect. The other side is adhesive coated, suitable for paper and board thermal lamination with digital machines.



#### TYPICAL TECHNICAL FEATURES (\*)

| PHYSICAL PROPERTIES                     |             | UNIT    | VALUE | METHOD     |
|---|-------------|---------|-------|------------|
| Thickness                               |             | μm      | 35    | Internal   |
| Yield                                   |             | m²/kg   | 31,20 | Internal   |
| Grammage                                |             | g/m²    | 32,05 | Internal   |
| COF (ultra-matt side / ultra-matt side) | dynamic     | -       | 0,70  | ASTM D1894 |
| Surface tension                         | coated side | dyne/cm | 46    | ASTM D2578 |

| THERMAL PROPERTIES     |               | UNIT | VALUE                  | METHOD   |
|------------------------|---------------|------|------------------------|----------|
| Lamination temperature | adhesive side | °C   | 110-130 <sup>(†)</sup> | Internal |

<sup>(†)</sup> variable according to the processing conditions

| OPTICAL PROPERTIES |     | UNIT | VALUE | METHOD     |
|--------------------|-----|------|-------|------------|
| Gloss (matt side)  | 45° | GU   | 6     | ASTM D2457 |

## **STORAGE**

Store the material in a dry location (preferably with RH < 50%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents.

Partially used reels have to be repacked as originally supplied.

#### WARRANTY

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly. It is recommended to condition the material at room temperature at least 24 hours before its use.

### **DISCLAIMERS**

MAG DATA Spa gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use.

Tel.: (0039) 0521525311 Fax:(0039) 0521525339 e-mail: <u>info@mag-data.com</u> sito web: <u>www.mag-data.com</u>

<sup>(\*)</sup> The information and data contained herein are to be used only as a guideline; therefore, MAG DATA Spa doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.



| Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purp | osed |
|--|------|
| with the type and level of its treatment.  |      |

e-mail:  $\underline{info@mag-data.com} \ sito \ web: \ \underline{www.mag-data.com}$