


BRUSHED SILVER WET 23μ

Brushed metallized polyester film with one side chemical coated to enhance the adhesion properties. The main application is paper and cardboard lamination to obtain a particular optical effect.

Product code: BRY023 Update: October 2020



TECHNICAL FEATURES

PHYSICAL PROPERTIES		TEST METHOD	UNIT	VALUE
Thickness		Internal	micron (μm)	23
Grammage		Internal	g/m ²	36
Yield		Internal	m²/kg	27,7
Coefficient of friction	Static	ASTM D 1894	-	0,42
	Dynamic		-	0,30
Surface tension	Plain side	DIN 53364	Dyne/cm	-
	Acrylic side			42

MECHANICAL PROPERTIES		TEST METHOD	UNIT	VALUE
Tanaila atuanath	MD	ASTM D 882	daN/mm ²	≥16
Tensile strength	TD			≥16
Elengation at break	MD	ASTM D 882	%	≥100
Elongation at break	TD			≥80

OPTICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Gloss at 60°	ASTM D 1003	GU	350
Haze	ASTM D 1003		-
Optical density	Internal	-	2,2

Storage: store in a dry and clean place far from heat sources and humidity (max 30°C and 55% of relative humidity). Do not expose rolls to direct sunlight. Protect the partially used rolls and keep a high stock rotation. The film should be allowed to reach operating room temperature 24 hours before use.

Note: trial tests are recommended before proceeding with full production run so as to verify the suitability of the product for its specific application. Verify the compatibility of the film with inks and adhesives. Please visit our web site for more details.

The values indicated represent the best of our knowledge and experience. They are provided simply as a matter of information, taking no responsibility on their absolute truthfulness. Values may be changed without notice. Mag Data S.p.A gives no warranty, expressed or implied, as to the suitability of the product for any specific application.

Mag Data – S.p.A. a socio unico

Strada della Selva 100 - 43052 Colorno (Pr) - Italy P. IVA/C.F. 02551830348 Tel.: (0039) 0521/525311 Fax: (0039) 0521/525339 E-mail: <u>info@mag-data.com</u> Sito web: <u>www.mag-data.com</u>