

TECHNICALTHIN MATT DRY - CTM022DATA SHEET

THIN MATT DRY - CTM022 is a matt bioriented polypropylene film with one side corona treated and the other side coated with adhesive, which is specifically designed for thermal lamination of printed or unprinted paper and cardboard.

MATT CORO	INA TREATED SIDE
POLYPROPYLENE	THERMOADHESIVE SIDE

TYPICAL TECHNICAL FEATURES (*)

PHYSICAL PROPERTIES		UNIT	VALUE	METHOD
Thickness		μm	22	Internal
Yield		m²/kg	51,8	ASTM D4321
Grammage		g/m²	19,30	Internal
Surface tension	corona side	dyne/cm	> 40	ASTM D2578
	adhesive side		> 40	
THERMAL PROPERTIES		UNIT	VALUE	METHOD
Lamination temperature		°C	100-120 ^(†)	ASTM D1204
(†) variable according to the processing conditions				

OPTICAL PROPERTIES		UNIT	VALUE	METHOD
Gloss (matt side)	45°	GU	< 10	ASTM D2457

STORAGE

Store the material in a dry location (preferably with RH < 50%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents. Partially used reels have to be repacked as originally supplied.

WARRANTY

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly. It is recommended to condition the material at room temperature at least 24 hours before its use.

DISCLAIMERS

MAG DATA Spa gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use.

^(*) The information and data contained herein are to be used only as a guideline; therefore, MAG DATA Spa doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.



Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purposed with the type and level of its treatment.