


**TECHNICAL  
DATA SHEET**

**PURE LEATHER WET - LDW025**

**PURE LEATHER WET – LDW025** is a bioriented polypropylene film, with a special leather effect coating on one side while the other side is corona treated.



*TYPICAL TECHNICAL FEATURES (\*)*

| PHYSICAL PROPERTIES |             | UNIT               | VALUE        | METHOD     |
|---------------------|-------------|--------------------|--------------|------------|
| Thickness           |             | µm                 | 25 ± 1,25    | Internal   |
| Yield               |             | m <sup>2</sup> /kg | 61,72        | Internal   |
| Grammage            |             | g/m <sup>2</sup>   | 16,20 ± 0,81 | Internal   |
| Surface tension     | corona side | dyne/cm            | ≥ 40         | ASTM D2578 |
|                     | coated side |                    | ≥ 40         |            |

| OPTICAL PROPERTIES |     | UNIT | VALUE              | METHOD     |
|--------------------|-----|------|--------------------|------------|
| Gloss              | 60° | GU   | 7,0 <sup>(§)</sup> | ASTM D2457 |

<sup>(§)</sup> The Gloss points are for orientation only, due to the uneven structure.

**STORAGE**

Store the material in a dry location (preferably with RH < 50%) at a constant temperature between 10°C and 30°C. Do not leave it exposed to direct sunlight or atmospheric agents. Partially used reels have to be repacked as originally supplied.

**WARRANTY**

Material processability is guaranteed up to 6 months since shipment date, as long as it is stored correctly. It is recommended to condition the material at room temperature at least 24 hours before its use.

**DISCLAIMERS**

MAG DATA Spa gives no warranty, expressed or implied, as to the suitability of the material for a specific application or characteristic use. An industrial homologation test of the material in actual conditions of purpose is always needed in order to verify its suitability for the specific application or characteristic use. Before using the material, it is advisable to check the compatibility of the inks and adhesives to be purposed with the type and level of its treatment.

<sup>(\*)</sup> The information and data contained herein are to be used only as a guideline; therefore, MAG DATA Spa doesn't offer any guarantee on their absolute truthfulness and doesn't accept any liability arising out of their use.